



DESCRIPTION

UNIMARC SMALTO MICACEO is an acrylic resin and lamellar extender based top coat which protects and decorates metallic supports.

Its Special Formulation Produces:

- Barrier effect: its particular lamellar structure creates parallel extended layers inside the film, which block the penetration of water and atmospheric agents.
- Shield effect: the micaceous iron oxide and aluminium present in the product prevent ultraviolet radiation from reaching the underneath layers, delaying the deterioration of the binder.

For its aesthetic characteristics the product can be employed on various surfaces in order to create fine aesthetic effects.

INSTRUCTIONS FOR USE

Can Be Applied On:

- Supports in properly pre-treated ferrous metal;
- Properly treated aluminium and light alloys;
- Galvanized surfaces;
- Plastic surfaces (PVC);
- Supports in new or already varnished wood.

TECHNICAL SPECIFICATIONS

- Type of Binder: synthetic resin in aqueous dispersion
- Pigments and extenders: micaceous iron oxides, aluminium -Solvent: water
- Specific gravity per UNI EN ISO 2811-1: $1,24 \div 1,28$ kg/l depending on the colours
- Viscosity on packing UNI 8902: 10.000 ± 1000 cps a 25 °C (Brookfield rotational viscosimeter)
- Drying times (at 25°C and 65% R.H.): touch dry in 1 hours; may be painted over after 4 hours

PREPARING THE SURFACE

Ferrous Metal:

- Employ mechanical or manual cleaning methods to remove any flakes which, as a result of lamination, are not perfectly adherent, along with all traces of rust.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface.
- Remove any grease from the surface using Nitro thinner 5170076.
- Eliminate all traces of dust and dirt.
- Apply 2 coats of UNIMARC PRIMER ANTIRUGGINE 3310107 on a perfectly dry surface, allowing at least 6

hours between coats.

- On surfaces particularly exposed to the elements, apply 2 coats of CROMO K70 series 194 synthetic rust inhibiting paint as an undercoat.
- Apply 2 coats of UNIMARC SMALTO MICACEO.

Aluminium and light alloys:

- Remove all traces of oxide by means of mechanical or manual cleaning.
- Carefully remove any grease using suitable alkaline solutions or thinner.
- Remove any layers of old paint which are not perfectly adherent and sand the whole surface in order to coarsen it.
- Remove all traces of dust and, on a perfectly dry surface, apply 2 coats of UNIMARC SMALTO MICACEO.
- On surfaces particularly exposed to the elements, apply 2 coats, as an undercoat, of UNIMARC ANTIRUGGINE 3310107 or PRIMER 1630307.

Plastic (PVC):

- Sand the surface in order to coarsen it slightly.
- Remove any grease using Nitro thinner 5170076 and clean the surface.
- Apply 2 coats of UNIMARC SMALTO MICACEO on a perfectly clean and dry surface.

Woodwork:

- Sand lightly in order to remove the raised wood fibres.
- Eliminate any coats of old flaking varnish and coarsen all the surfaces which have already been varnished.
- Remove any resin using the Nitro thinner 5170076.
- Fill the imperfections with synthetic filler. Rub down the fillings and eliminate any dust.
- Apply 2 coats of primer UNIMARC FONDO UNIVERSALE 3350019 on a clean, dry surface, allowing at least 6 hours between coats or using mat primer MARCONOL ORIENTALITE 1450519.
- Sand the surfaces and then proceed with the application of 2 coats of UNIMARC SMALTO MICACEO

APPLICATION INSTRUCTIONS

- Condizioni dell'ambiente e del supporto:
Temperatura dell'ambiente: Min. +8 °C / Max. +35 °C
Umidità relativa dell'ambiente: <75%
Temperatura del supporto: Min. +5 °C / Max. +35 °C
Umidità del supporto: <10%
Dry surfaces
- Tools: brush, roller or sprygun.

- Diluting: with water
by brush and roller ready to use or at 5% max
by spraying at 15%.
- N. coats: at least 2 coats.
- Tools should be cleaned with water immediately after use.
- Indicative spreading rate: 6-7 sq m/l based on 2 coats.

any previously existing sheets. For further technical information call the technical service +39 041 4569322

TINTING

Colors are obtainable via the Marcromie color matching system and using COLORADO series 548 colorants.

When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.

STORAGE

Maximum storage temperature: +30° C

Minimum storage temperature: +5° C

Stability in the original unopened containers and with suitable temperature conditions: 3 years.

SAFETY RULES

EU limit value (Dir. 2004/42/EC)

Cat. D: Interior/exterior trim and cladding paints for wood, metal or plastic (water-base): 150 g/l (2007) / 130 g/l (2010)
UNIMARC SMALTO MICACEO Contains max: 130 g/l VOC

The product does not require labelling per the provisions of 67/548/CEE and 1999/45/CE and subsequent changes and amendments. Use the product according to current health and safety regulations; after use, do not discard the containers in the environment; allow the residue to dry thoroughly, then treat as special waste. Store out of the reach of children. Use in a well ventilated place. In case of contact with eyes, wash immediately with abundant running water. In caso of ingestion, see a physician immediately and show him or her the container or label. Do not dispose of residues in the sewers, waterways or ground.

For more information consult the safety data sheet.

SPECIFICATION ITEM

Water soluble acrylic protector with a micaceous effect for indoor or outdoor use Application, on prepared surfaces of UNIMARC SMALTO MICACEO, synthetic resin in aqueous dispersion based, in the quantities determined by the absorption of the support.

Supply and laying of the material.....per sq. m.

COLORIFICIO SAN MARCO guarantees that the information herein is provided to the best of its technical and scientific knowledge and based on its experience; nonetheless, the company may not be held liable for the results obtained using these products, as application conditions are beyond its control. It is recommended to always make sure that the product is suited to each specific instance. The present sheet voids and replaces